

Organic Pigments for Paints and Coatings

Technical datas for pigment card

| Product name | Full Shade (5%) | Tint (5:95) | C.I. | Heat | Light | Weather | Automotive Refinishing | Industrial Paints | Powder Coatings | Decorative Paints |
|-------------------------|-----------------|-------------|---------|------|-------|---------|------------------------|-------------------|-----------------|-------------------|
| IQC Coat Yellow 74-T | | | PY 74 | 180 | 7 | 3-4 | | ● | | ● |
| IQC Coat Yellow 74-O | | | PY 74 | 180 | 7 | 3-4 | | ● | | ● |
| IQC Coat Yellow 83-T | | | PY 83 | 200 | 7 | 2-3 | ○ | ● | ● | ○ |
| IQC Coat Yellow 83-O | | | PY 83 | 200 | 7 | 3 | ○ | ● | ● | ○ |
| IQC Coat Yellow 139 | | | PY 139 | 280 | 7-8 | 4 | ● | ● | ● | ● |
| IQC Coat Yellow 151 | | | PY 151 | 160 | 8 | 5 | ● | ● | ● | ● |
| IQC Coat Yellow 154 | | | PY 154 | 180 | 8 | 5 | ● | ● | ● | ● |
| IQC Coat Yellow 155 | | | PY 155 | 180 | 8 | 4-5 | ● | ● | ● | ● |
| IQC Coat Orange 34 | | | PO 34 | 200 | 6 | 2-3 | | ● | ● | |
| IQC Coat Orange 36 | | | PO 36 | 180 | 8 | 4-5 | ○ | ● | ● | ● |
| IQC Coat Red 484 FBL | | | PR 48:4 | 180 | 6 | 3 | | ● | | ● |
| IQC Coat Red 112-T | | | PR 112 | 170 | 7 | 3-4 | | ● | | ● |
| IQC Coat Red 112 FGR | | | PR 112 | 200 | 7 | 3-4 | | ● | | ● |
| IQC Coat Quindo Red 122 | | | PR 122 | 250 | 8 | 4-5 | ● | ● | ○ | ● |

● main use ○ limited suitability, to be tested before use * Full shade 2.5%

| Product name | Full Shade (5%) | Tint (5:95) | C.I. | Heat | Light | Weather | Automotive Refinishing | Industrial Paints | Powder Coatings | Decorative Paints |
|------------------------------|-----------------|-------------|--------|------|-------|---------|------------------------|-------------------|-----------------|-------------------|
| IQC Coat Red 2B 170 | | | PR 170 | 180 | 8 | 3-4 | ● | ● | ● | |
| IQC Coat Red 3B 170 | | | PR 170 | 180 | 8 | 3-4 | ○ | ● | ● | |
| IQC Coat Red 5B 170 | | | PR 170 | 180 | 7-8 | 2-3 | | ● | ● | |
| IQC Coat Red A3B 177 | | | PR 177 | 250 | 8 | 4 | ● | ● | ● | |
| IQC Coat Red 188 | | | PR 188 | 200 | 7 | 3-4 | | ● | ○ | ○ |
| IQC Coat DPP Red 254 2030 | | | PR 254 | 250 | 8 | 4-5 | ● | ● | ● | ○ |
| IQC Coat DPP Red 254 BO | | | PR 254 | 250 | 8 | 5 | ● | ● | ● | ○ |
| IQC Coat Quindo Violet 19 RY | | | PV 19 | 200 | 8 | 4-5 | ● | ● | ○ | ○ |
| IQC Coat Quindo Violet 19 RV | | | PV 19 | 250 | 8 | 4-5 | ● | ● | ○ | ○ |
| IQC Coat Violet 23 R* | | | PV 23 | 180 | 7-8 | 4-5 | ● | ● | ● | ● |
| Coat Violet 23 B-Special* | | | PV 23 | 180 | 7-8 | 4-5 | ● | ● | ● | ● |
| IQC Coat Blue A3R 60 | | | PB 60 | 300 | 8 | 4-5 | ● | ● | ● | ● |
| IQC Coat Green 7 | | | PG 7 | 250 | 7 | 4-5 | ● | ● | ● | ● |
| IQC Coat Green 36 | | | PG 36 | 300 | 7-8 | 5 | ● | ● | ● | ● |